



PermaTherm | EPS Panels Insulated Metal Panels

Thermal Resistance Values

Panel Thicknesses	R-Value	K-Factor
2 in.	8.70	.23
3 in.	13.05	.23
4 in.	17.40	.23
6 in.	26.10	.23
8 in.	34.80	.23
10 in.	43.50	.23
12 in.	50.04	.23

** All values are calculated using core material of Type 1 (1 lb. Density) EPS Foam. Greater values can be reached with higher density foam which is available. At 25 degrees.*